

BITUMEN 60/70			
B.NO:08007			
NO	Property/Unit	Specification	TEST METHOD
1	Specific Gravity, 25/25 °C	1.010-1.060	ASTM D70
2	Penetration, 25°C ,25	60-70	ASTM D5
3	Softening point (°C)	49-56	ASTM D36
4	Ductility, 25 °C	100 min	ASTM D113
5	Loss on heating (wt %)	0/2 max	ASTM D6
6	Drop-in penetration after heating (%)	20 max	ASTM D6 & ASTM D5
7	Flash point (°C)	>250°C	ASTM D92
8	Solubility in THC (wt %)	>99,5	ASTM D4
9	Spot test	Negative	*A.A.S.H.O.T 102